

1450 Incompatibility of Oxalate Desensitizers with Acidic, Fluoride-Containing Total-Etch Adhesives

[C.K.Y. YIU](#)¹, N.M. KING¹, B.I. SUH², L.J. SHARP³, R.M. CARVALHO², D.H. PASHLEY⁴, and F.R. TAY⁵, ¹University of Hong Kong, China, ²Bisco, Inc, Schaumburg, IL, USA, ³University of Sao Paulo, Bauru, SP, Brazil, ⁴Medical College of Georgia, Augusta, USA, ⁵University of Hong Kong, Hong Kong

Purpose: To compare the microtensile bond strengths (μ TBS) of four single-bottle, total-etch adhesives of different acidity to oxalate desensitizer-treated acid-etched dentin and to examine the ultrastructure of the bonded interfaces. **Methods:** Flat coronal dentin from 84 extracted human third molars were bonded with One-Step (OS, Bisco), Single Bond (SB, 3M ESPE), OptiBond Solo Plus (OB, Kerr) and Prime&Bond NT (PB, Dentsply) after: [1] acid etching; [2] acid etching followed by BisBlock (BB, Bisco) application for 30s and [3] acid etching followed by Super Seal (SS, Phoenix Dental Inc.) application for 30s. Composite build-ups were performed using Filtek Z250 (3M ESPE). After storage for 24h, composite-dentin beams of 0.8mm were obtained for μ TBS testing. Representative fractured beams from each group were prepared for fractographic analysis using SEM and energy dispersive X-ray spectrometry (EDX). Undemineralized, unstained, epoxy resin-embedded sections were prepared for TEM after immersion in 50 wt% ammoniacal silver nitrate solution for 24h. The pH and F concentration of the adhesives were also measured. **Results:** μ TBS ($X \pm SD$, n=40 in MPa; Kruskal-Wallis/Dunn's). For each column, different superscripts indicated difference at $p < 0.05$.

Adhesives	pH	F concentration (ppm)	Adhesive only, no desensitizer	BB plus adhesive
OS	4.60	70	48.7 \pm 4.2 ^a	43.4 \pm 4.8 ^a
SB	3.60	130	47.4 \pm 4.2 ^a	39.6 \pm 8.1 ^a
OB	2.81	4527	49.2 \pm 7.3 ^a	12.6 \pm 8.6 ^b
PB	2.68	3641	51.8 \pm 4.5 ^a	6.9 \pm 10.6 ^b

SEM and TEM revealed numerous spherical globules on OB and PB bonded, desensitizer-treated dentin, but not in OS or SB. EDX analysis showed that they were composed not only of Ca and F, but also P and O. **Conclusions:** Oxalate desensitizers such as Super Seal and BisBlock cannot be used with Prime&Bond NT and OptiBond Solo Plus after acid-etching, as formation of calcium-fluoride like globules interferes with dentin hybridization and compromises bond strength.

[Seq #177 - Effects of Components and Agents](#)

10:45 AM-12:45 PM, Friday, 11 March 2005 Baltimore Convention Center 337

[Back to the Dental Materials: I - Adhesion-Composite Bond Strength Program](#)

[Back to the IADR/AADR/CADR 83rd General Session \(March 9-12, 2005\)](#)