

Kenneth K.Y. Wong* and Xuelai Liu

Nanotechnology meets regenerative medicine: a new frontier?

Abstract: Regenerative medicine is the creation of a tissue or organ with normal structures and functions to replace the lost or impaired ones via biological modulation and tissue engineering. Indeed, many researchers have focused on exploring new techniques or approaches in this field. In recent years, numerous nanotechnologies have been incorporated into the field of regenerative medicine, aiming to replace tissues. The application of nanotechnology is important as many nanomaterials exhibit novel biological properties in the modulation of cellular events. The two main directions in this field are to provide biologically compatible scaffolds as an optimal environment for cell migration and proliferation; as well as to attempt to induce stem cell recruitment and differentiation. Thus, this review will focus on these two aspects, briefly describing the clinical applications.

Keywords: healing; nanoparticles; regeneration; scaffold; wound repair.

*Corresponding author: **Kenneth K.Y. Wong**, LKS Faculty of Medicine, Department of Surgery, The University of Hong Kong, Hong Kong, China, e-mail: kkywong@hku.hk
Xuelai Liu: LKS Faculty of Medicine, Department of Surgery, The University of Hong Kong, Hong Kong, China

1 Introduction

Nanotechnology is defined by the use or the manipulation of materials ranging from 1 to 100 nm [1]. The rapid development of nanotechnology in the past decade has resulted in expanding its applications into medical areas and has established itself into a new subbranch termed as nanomedicine [2, 3]. At the nanoscale, materials can interact and regulate the cellular/tissue events at the molecular level. Currently, nanomedicine is leading the way to a new perspective and advances in biomedical study and clinical application, including diagnostic imaging [4, 5], anti-inflammation/anti-infection [6, 7], cell therapy, and nano cryosurgery/laser surgery [8, 9], as well as the anti-cancer drug delivery systems or devices [10–13].

Furthermore, numerous nanotechnologies have also been incorporated into the field of regenerative medicine in recent years, aiming to replace cells or tissues lost, for example, after trauma, ischemic stroke, or myocardial infarction [14]. Indeed, wound repair and regeneration occur in any tissue and organs after injury to some extent. This is more apparent in the skin in daily life as it is the largest organ in the body and has the largest exposed area to the outside. The study of tissue repair and healing in the skin and bone after wounding plays an essential role in advancing knowledge in regenerative medicine. Nanotechnology can contribute to tissue regeneration in various ways, involving enhanced cell adhesion and proliferation/migration, improvement in growth factor production and delivery, provision of scaffold for cell repopulation, as well as induction of stem cell differentiation [15, 16]. This review will focus on the use of nanofiber scaffold in tissue engineering and nanotechnology-mediated effects on stem cells in wound regeneration, as well as their potential clinical applications.

2 Regenerative medicine

Tissue repair and regeneration are essential biological processes during wound healing. Conventional therapy for improving tissue repair after injury includes topical application of antibacterial drugs, to help maintain a relatively clean environment. This would allow the physiological process of healing to take place under normal conditions [17–19]. Nonetheless, for large wounds or those severe traumas with more tissue defects, the use of conventional therapy has not been universally successful, as regeneration of complex structures requires dramatic changes in cellular behavior. Many researchers have, thus, focused on exploring new techniques or approaches to enhance regeneration and function restoration in such severe wounds. Indeed, recent studies have shown that the promotion of cellular proliferation, migration, and differentiation could enable effective repair and regeneration, if used in the appropriate context [20, 21].

The definition of regenerative medicine is the creation of tissue or organ with normal structures and functions

to replace the lost or impaired ones via biological and tissue engineering [22]. In this regard, the two main directions in the development of this field are to provide biologically compatible scaffolds as an optimal environment for cell migration and proliferation, as well as to attempt to induce stem cell recruitment and differentiation [23]. Recent advances in nanotechnology have been effective in incorporating scaffold in tissue engineering and stem cell science [24], thus, expanding into the realms of regenerative medicine (Figure 1). The major applications of various nanomaterials currently being used in regenerative medicine are scaffolds, delivery devices, and applications for cellular modification.

3 Nanofiber scaffolds in tissue engineering

Tissue engineering involves the fabrication of scaffolds from synthetic and natural polymers through a variety of processing methods to act as biologically active substitutes for tissues and organs [25, 26]. Its initial theories and techniques of *in vitro* tissue constructs have already expanded with the development of the incorporation of nanotechnology. Indeed, the design and construction of the scaffolds are under intensive research in recent years, and its basic and important strategy is to construct biocompatible scaffolds, in combination with living cells and/or bioactive molecules, with the aim to replace, regenerate, or repair damaged cells or tissue [27, 28].

An ideal scaffold should have similar stromal properties comparable to target tissue. It should also have




Figure 1 Schematic diagram demonstrating multidisciplinary sciences are involved in wound regenerative medicine. The advance of nanotechnology further innovates the development of various sciences.

biocompatibility and permeability, controlled porosity, as well as support for cell attachment and proliferation. In this way, subsequent cell adhesion and growth will be greatly enhanced, and thus, acceleration of tissue repair and wound regeneration will be prompted. In this regard, nanotechnology-derived scaffolds have been proven to possess specific physiochemical properties [29, 30], satisfactory biocompatibility [31–33], improved permeability [34, 35], and adjustable porosity [36–38]. Moreover, recent study also indicated that nanotechnology could control the scaffold to have better nanotopographies, with which the surface roughness would further enhance cell attachment and spreading [39]. Zhu et al. regarded that an enlarged surface area of nanostructured materials in the scaffold would absorb and attach more adhesive proteins including fibronectin and vitronectin, which would increase cell-cell interactions, and tissue regeneration, as well as following the repair process in healing [40].

3.1 Biochemical properties of nanofiber scaffolds

The chemical properties of various nanofiber scaffolds all mimic the fibrous architecture of the extracellular matrix (ECM) in normal tissues [41–43]. For instance, collagen types I, II, III, and IV, as the main ECM in the skin and bone tissues, are the most abundant natural polymers in the human body (Figure 2). They provide cells not only with the appropriate microenvironment for growth and tissue regeneration but also function to impart structural integrity and strength. As a result, collagen has been




Figure 2 Masson trichrome of normal skin. Staining showed the distribution and density of collagen protein in the skin dermal layer. Under this staining, collagen protein was stained blue, the nuclei were stained black and background (muscle, cytoplasm and keratin) (200 \times).

utilized widely to fabricate nanofiber scaffolds. In addition, other natural polymers, including globular proteins and elastin, and synthetic polymers, such as poly (glycolic acid) (PGA), poly (lactic acid) (PLA), poly (lactic-co-glycolic acid) (PLGA), polydioxanone, and polycaprolactone, have also been used [44].

Regarding the processing of nanofiber scaffolds, electrospinning and self-assembly techniques have been employed to fabricate for the regeneration of bone, skin, cartilage, and cardiac as well as nervous tissues [45].

3.2 Electrospun nanofiber scaffolds

Electrospinning is a widely used technique for the production of nanofiber scaffolds. It is a controllable technique through adjusting processing conditions and polymer properties. The nanofiber scaffold properties can be changed according to the practical requirement, especially for the size, porosity, surface topography, biodegradability, solubility, and mechanical function. These advantages make it possible to modify the spatial alignment and orientation, by which cell adhesion and proliferation as well as growth are directed and controlled [46].

Just like other nanomaterials, the electrospun nanofiber scaffolds have larger surface to volume ratio, which directly increases the exposure area to the surrounding cells. Therefore, they can be adapted to modulate the cellular event to promote proliferation, differentiation, and migration. Meanwhile, the larger area of these nanofiber scaffolds also increases the capability of cell adhesion. Furthermore, recent studies also indicated that these nanofibers could be also used to deliver various drug molecules, genes, and peptides, thus further enhancing cell regeneration.

During the exploration of the functionalization strategies to improve the delivery efficacy of the nanofiber scaffolds, the idea of coelectrospinning of the active surface agents and polymers, and the immobilization of bioactive ligands, have been sprung [47]. These could more effectively control the delivery efficacy. Meanwhile, the utilization of composites to control the shape of the nanofiber scaffolds has also been demonstrated to enhance the delivery of drug and biomedical properties. In this regard, Zhang et al. synthesized electrospinnable bioactive macromolecules (collagen and fibronectin) as the shell and a synthetic polymer with mechanical and structural properties as the core [48]. This functionalized composite scaffold, on one hand, enables cell growth and differentiation; on the other hand, the controlled release of encapsulated drugs further contributes toward cell regeneration and tissue repair.

Sahoo et al. targeted the natural ECM to fabricate into electrospun nanofiber scaffolds and deposited β -fibroblast (FB) growth factor, an important growth factor involved in mesenchymal stem cell proliferation and differentiation in tissue repair. Their study indicated that the electrospinning technique could effectively prolong the growth factor release from the scaffolds, and a sustained release positively influenced the stem cell behavior and fate [49]. Liu et al. further investigated the feasibility of incorporating neurotrophin-3 and chondroitinase ABC onto the electrospun collagen nanofibers for the treatment of spinal cord injuries. Their results showed that it was feasible to promote nerve regeneration through the provision of topographical signals and multiple biochemical cues arising from both nanofiber scaffolds and attached cytokines [50].

The traditional electrospinning technique is mainly for the fabrication of the 2-D nanofibrous solution or sheet. However, the size of the pores is, in general, too small for cell infiltration, resulting in the less protein absorption and cell adhesion. The seeded cells tend to grow in a monolayer on the surface of the mesh [14]. In recent years, research has been focused in producing 3-D nanofiber scaffolds for both *in vitro* and *in vivo* studies and applications, aiming to improve cell infiltration. Yang et al. explored a 3-D multilayered cell-nanofiber scaffold with alternating layers of human dermal FBs or keratinocytes seeded on PCL/collagen nanofibrous sheets. The results indicated that both kinds of cells seeded could effectively proliferate and contribute to the formation of new ECM, which would indicate the potential to be a substitute of the skin [51].

Horne et al. demonstrated that when compared to the classical 2-D cultureware, the modified 3-D electrospun poly- ϵ -caprolactone (PCL) nanofiber scaffolds were more superior in enhancing *in vitro* proliferation and differentiation of cortical cells. When neurotrophin, brain-derived neurotrophic factor (BDNF) were tethered onto the modified 3-D scaffolds, they further found neural stem cell proliferation and differentiation toward neuronal and oligodendrocyte lineages, indicating that modified PCL nanofiber 3-D scaffolds were capable of supporting neural stem cells and their derivatives [52]. Furthermore, Hurley et al. cocultured human microvascular endothelial cells (ECs) and FBs in peptide-made 3-D nanofiber scaffolds for up to 6 days and found that FBs in scaffolds enhanced capillary network formation by improving EC migration and increasing vascular endothelial growth factor and angiopoietin-1 expression in a temporal manner, while EC-FB interactions attenuated FB matrix metalloproteinase-2 expression and increased collagen I deposition, resulting in better construct stiffness and a more stable

microenvironment in cocultures [53]. This finding supported cell-cell interactions, and cell migration in 3-D nanoscaffolds contributed to an optimal environment for regeneration and tissue repair.

3.3 Self-assembling nanofiber scaffolds

In addition to electrospun nanofiber scaffolds, self-assembling nanofiber scaffolds provide another intensive research target in scaffold fabrication [54]. When topically applied onto the wound, these self-assembling nanofiber scaffolds would encourage wound edge tissue contraction. Furthermore, addition of functional ligands to the self-assembling peptides could enhance scaffold self-assembling effect.

Davis et al. designed a self-assembling peptide nanofiber scaffold for prolonged delivery of insulin-like growth factor 1 (IGF-1), a growth and differentiation factor for cardiomyocyte, to the myocardium using a biotin sandwich approach. After injection into the rat myocardium, the scaffolds provided sustained IGF-1 delivery for 28 days. When combined with transplanted cardiomyocytes, IGF-1 delivery by the scaffolds decreased caspase-3 cleavage and increased the myocyte cross-sectional area, through which systolic function was improved in an experimental myocardial infarction model [55].

Segers et al. also targeted stromal cell-derived factor-1 (SDF-1), which is a well-characterized chemokine for attracting stem cells and, thus, an ideal candidate for promoting regeneration, to investigate the efficacy of self-assembling nanofiber scaffolds containing SDF-1 on myocardial stem cell regeneration. They designed a chemokine named S-SDF-1 (S4V) that was resistant to matrix metalloproteinase-2 and exopeptidase cleavage but retains chemotactic bioactivity, thereby reducing the neurotoxic potential of native SDF-1. Self-assembling peptides were used to entrap and deliver S-SDF-1 (S4V). Their results demonstrated a nanofiber scaffold-induced delivery that promoted recruitment of stem cells and improved cardiac function in the myocardial infarction area [56]. This suggested that the chemotaxis of stem cells could be a promising strategy for tissue regeneration.

In addition to the above nanoscaffolds, some protein- and peptide-modified synthetic polymeric biomaterials were also used for the tissue regeneration and repair, including hydrogels based on protein-protein interactions and conformational changes of a protein. These conjugations at nanolevel of polymeric and protein/enzyme, not only were used as an ideal delivery system for macromolecules for cell adhesion but also provide a better “niche”

to release important cytokines to local tissues [57]. Thus, these nanomaterials could further promote tissue repair due to their protein-protein interactions and conformational changes of a protein.

The 3-D printing technology is another area of intensive research in tissue engineering-mediated regeneration and repair. For example, this technology now enables the accurate 3-D organization of some components, which are important for bone formation, involving graft porosity and vascularization [58]. In this regard, bone printing is regarded as a promising therapeutics in orthopedics because it combines rapid prototyping technology to produce a scaffold of the desired shape and internal structure with the incorporation of multiple living cell types that can form the bone tissue once implanted [59].

4 Nanomedicine and effects on stem cells

The biomedical effect of nanoparticles on stem cells in wound is another important direction in regenerative medicine. Stem cells exist in most of the tissues and organs in the human body, including the skin and bone, cardiac tissue, etc. Even after severe injury, a few stem cells can still be found remaining in the local environment. These can proliferate and, together with the recruitment of the circulating stem cells, help in tissue repair. For example, in the skin, both the epidermal and dermal layers contain a subgroup of stem cells in each layer (Figure 3). These epidermal stem cells in the skin include two parts: the epithelial stem cells, found in the epithelial basal layer, and the bulge stem cells, located in the hair follicle [60]. The




Figure 3 Schematic diagram showing the histological structures in the skin. The skin is composed of epidermal and dermal layers containing stem cell niches (blue: epidermal stem cells; red: dermal mesenchymal stem cells).

hair follicle consists of three anatomical structures involving the outer root sheath, inner root sheath, and hair shaft (Figure 4), the bulge stem cells are a group of specific cell population outer root sheath and have the potential to proliferate and differentiate into keratinocytes after wounding [61, 62]. When the epidermal tissue is damaged, the bulge stem cells can migrate to the epidermal layer to differentiate [63] (Figure 5). These populations of stem cells have self-renewing potential and amplify rapidly in response to skin injury and further undergo several cell divisions for the reconstruction of the epidermal barrier [64, 65]. For the dermal mesenchymal stem cells, they have been successfully isolated from the mouse and human skin [66, 67] and could be induced to form FBs, cardiomyocytes, adipocytes, and neurons [68, 69]. Furthermore, stem cell grafting is a specific technique for those wounds with severe damaged tissue or loss. The combination of nanotechnology with stem cell science may provide a new therapeutic approach for regenerative medicine.

4.1 Nanoparticles and stem cells differentiation

Stem cells in the undifferentiated state have the unique ability to differentiate into various kinds of cell types and the potential to develop into tissues eventually. They can be activated under the influence of drug molecules or cytokines. For the skin, the epidermal stem cell differentiation toward the keratinocyte lineage will contribute to the re-epithelization process during wound regeneration. The underlying signaling mechanisms of skin cell regeneration are beginning to be understood. Nguyen




Figure 4 HE staining of normal skin hair follicles. Staining showed the anatomical structures of transverse section in hair follicles, including the outer root sheath (ORS), inner root sheath (IRS), and hair shaft (HS) (400×).

et al. reported that Notch/p63 cross-talk played an essential role in the differentiation of skin stem cells into keratinocytes [70]. Schafer and Werner found that c-myc knockout mice with the absence of the stem cells in the skin epidermal basal layer would display delayed re-epithelization [71]. This would support that c-myc was a regulator of the skin epidermal stem cell fate [72]. Apart from Notch and c-myc, Wnt/ β -catenin [73, 74] and the Hedgehog signaling pathway [75, 76] have also been implicated in stem cell differentiation during skin regeneration.

Some nanoparticles have the potential to promote the differentiation of stem cells. For instance, Tian et al. reported that the topical application of silver nanoparticles (AgNPs) could accelerate healing in a burn wound model and that regenerated hair follicle tissue could be observed in the granulation tissue in AgNP-treated mice [77]. This finding would suggest that AgNPs might trigger various types of skin stem cell differentiations. Following this, we also observed a faster differentiation of keratinocytes deriving from skin stem cells during regeneration [78]. Moreover, others have also observed the concentration-dependent activation of human mesenchymal stem cells (hMSC) by AgNPs [79], which suggested that the ECM remodeling process in healing could be optimized through the effects of AgNPs, with consequent enhancement of the quality of healed skin.

For the bone injury, boron-containing compounds were shown to have the potential to contribute to osteoblast regeneration. Wu et al. explored boron-containing mesopore bioactive glass (B-MBG) scaffolds and evaluated the response of osteoblasts to these scaffolds. Meanwhile, the effect of dexamethasone (DEX) delivery in B-MBG scaffold system on the proliferation, differentiation, and bone-related gene expression of osteoblasts were also investigated. Their experiment suggested that boron-containing nanoparticles promoted osteoblast proliferation and contributed to the DEX release from the MBG scaffolds. Their study also suggested that the potential differentiation of the MSC induced by this nanoscaffold system into the osteoblasts was another factor contributing to bone tissue regeneration [80].

4.2 Nanotechnology-based microenvironment enhances stem cell differentiation

Stem cell niches are the microenvironment to the resident, maintenance, and development in cell circle. In recent years, intensive research targeted the creation of stem cell microenvironment to modulate cellular proliferation, differentiation, and maturation. In this regard, studies focused on the utilization of nanotechnology to mimic the




Figure 5 Schematic diagram showing the epidermal stem cell in the skin. Epithelial stem cells and bulge stem cells, respectively, distribute in the skin epithelium basal layer and in the outer root sheath in hair follicles (pink: epithelial stem cells; red: bulge stem cells).

in vivo stem cell microenvironment for the investigation of the mechanisms underlying the differentiation into different cell types [81].

Silva et al. utilized biologically compatible self-assembling peptide nanofiber scaffold (SAPNS) to create the ECM and used them for the neural cell regeneration. They found an effective migration of neural stem cells and growth of blood vessels in this scaffold [82], which suggested that SAPNS could establish a better 3-D microenvironment for the migration and differentiation of stem cells. Gelain et al. also reported the development of a 3-D cell culture system using the peptide nanofiber scaffold with mouse adult neural stem cells. They attached several functional motifs to self-assembling peptide RADA16. These functionalized peptides underwent self-assembly into nanofiber scaffolds similar to matrigel, and cells were fully embedded in the 3-D environment of scaffold. The results from gene expression profiling array experiments showed better neural stem cell adhesion and differentiation [83].

In recent years, Srouji et al. explored the effects of nanoscaffold on hMSC differentiation. It was found that this 3-D electrospun porous scaffold (composed of poly ϵ -caprolactone and collagen) could support hMSC cell attachment and proliferation with better distribution. When these nanoscaffolds were subcutaneously implanted into nude mice, good integration with surrounding tissues and neovascularization were seen [84]. Taken together, the combination of nanotechnology and stem cell science will bring promise for the wound regenerative medicine.

4.3 Biological effect of nanotechnology on various types of stem cells

Nanotechnology-mediated delivery of biomolecules, including proteins/enzyme, growth factors, and cytokines present an excellent tool to control the differentiation of stem cells. Some biocompatible nanoparticles can gain access into stem cells and activate signaling cascades.

For the embryonic stem cells (ESCs), Ferreira already reported that the incorporation of these polymeric nanoparticles had a large impact on the differentiation in the human ESCs [85]. Sridharan et al. explored the use of a composite collagen carbon nanotube material as an *in vitro* cell culture matrix to induce early differentiation of human ESC to neural progenitor cells. They used carboxyl-modified single-walled carbon nanotubes (SWCNTs) to obtain a composite material with type I collagen. They found that carboxyl-modified SWCNTs contributed to the early differentiation of ESCs into neural progenitor cells [86]. Chao et al. found that polyacrylic acid (PAA) grafted onto carbon nanotubes has the ability to differentiate human ESCs into neurons, and when they grafted a new 2-D thin film composed of PAA onto the carbon nanotubes, they found that the differentiated neurons were more mature than those on the pure PAA control surfaces due to the lower levels of neural differentiation. Furthermore, this new type of thin-film scaffold enhanced ESC proliferation and adhesion [87]. In the following study, they targeted the ability of PAA-grafted MWCNTs, pure MWCNTs, as well as MWCNTs functionalized by polymethacrylic

acid (PMAA) in various differentiation potential of human ESCs into neuronal cells [88]. The results further suggested that carbon nanotubes could enhance cell adhesion and growth factor adsorption, as well as stem cell differentiation. In addition to the ESCs, modern regenerative medicine research has been targeting the generation of patient-specific induced pluripotent stem cell (iPSC) lines [89]. Indeed, the protocol for the derivation of neural crest cells from human iPSCs has been developed [90, 91], which indicated that these could be induced to differentiate toward the neuron, while nanotechnology will continue to contribute to the induction and differentiation.

For the mesenchymal stem cells, they have the ability to differentiate into several specific cell lineages in the local microenvironment [92]. Voge and Stegemann found that nanotopography provided by carbon nanotubes could influence the mesenchymal stem cell differentiation [93]. Furthermore, the nanofiber scaffold fabricated by the electrospinning technique was indicated to be matrix conducive to the differentiation of hMSCs into hepatocyte-like cells, and the expression levels of liver-specific markers (albumin, α -fetoprotein) were higher, demonstrating that the nanofiber scaffolds enhanced hMSC differentiation into a hepatocyte lineage [94]. Their study suggested that the differentiation of mesenchymal stem cells induced by nanotechnology might be used in the treatment of liver failure. While for the neural stem cell, Kam et al. explored the influence of laminin-SWCNTs films on neural stem cells, their study indicated that compared with pure laminin substrates, laminin-SWCNT films could enhance the growth and proliferation of neural stem cells; moreover, layer-by-layer of films consisting of SWCNTs and laminin could promote their adhesion and differentiation, like that of the presence of large amounts of differentiated neurons and glial cells. These results suggested that thin composite SWCNT-laminin films can be employed as materials in the foundation of neural electrodes to long-term integration with neural tissue [95].

5 *In vivo* applications of nanotechnologies in regenerative medicine

5.1 Skin tissue regeneration and wound dressing

For the nanofiber scaffolds, enhanced cell adhesion and proliferation due to larger surface, better local adsorption

of wound liquids due to controllable porosity, and comparability to ECM, make it possible to be used as wound dressing. Meanwhile, these nanofiber scaffolds also have the potential to deliver various drug molecules to the wound site, which can further contribute to the wound tissue regeneration and repair. For example, some nanofiber scaffolds could deliver antibiotics [96–99], some nanoparticles have antibacterial properties [100–102], and some contain cytokines [103], as well as growth factors [104]. Khil et al. initially explored the coating of polyurethane membrane on wound dressing using electrospun nanofibrous technique. Their study indicated that this wound dressing led to an increased rate of epithelialization and dermis organization in wound tissue [105]. In a subsequent study, Chen and Chiang modified the polyurethane membrane by adding AgNPs [106]. The polyurethane membrane's antimicrobial activity improved to approximately 100% and suggested that this modified product was a better collagen sponge wound dressing.

In theory, any polymer with better biocompatibility and antibacterial properties can be conjugated to nanofiber scaffolds for the fabrication of wound dressing. For instance, chitosan is a natural biodegradable polymer with ideal biocompatibility, antibacterial, hemostatic, as well as wound-healing properties [106, 107]. Meng et al. found an improved healing of deep second-degree burns in rats using wound dressing coated with RADA16-I peptide self-assembling nanofiber hydrogel scaffolds [108]. Zhou et al. used electrospun carboxyethyl chitosan/polyvinyl alcohol to construct wound dressing and found that the electrospun matrix could be used as a potential wound dressing for skin regeneration [109]. This finding was further supported by the Kang et al. study [110]. Other candidates for wound dressing applications include silk fibroin/hydroxybutyl chitosan nanofibrous scaffolds. They have also been shown to have a good biocompatibility with better cell viability and fast skin wound healing rate [111, 112].

5.2 Bone regeneration

Bone is a mineralized organic matrix composed of collagenous fibers and calcium phosphate and exists in the format of hydroxyapatite (HA). A large amount of osteoblasts, osteocytes, and osteoclasts are embedded in the bone tissue, which is endowed with both elasticity and hardness. Therefore, in terms of designing the bone scaffolds in reconstruction, several factors need to be considered. These include suitable biophysical properties (elastics and hardness), porosity to support cell growth,

and differentiation [14]. Furthermore, for those nanoscaffolds with delivery function, the releasing kinetics of drug molecules from scaffolds and sustainability of cellular differentiation also need to be considered. In this regard, osteoblast ossification induced by nanofiber scaffolds has been investigated in various HA composites, including with collagen [113–115], PLA [116], and PLGA [117, 118]. Furthermore, Gentile and Zou explored HA/gelatin composite nanoscaffolds in both *in vitro* and *in vivo* experiments and found that these nanoscaffolds could effectively promote osteoblast proliferation and adhesion, and the ossification process was accelerated [119, 120].

Li et al. targeted silk fibroin fiber scaffolds containing bone morphogenetic protein 2 (BMP-2) to explore the effect on hMSCs. They found that the scaffold could support hMSC growth and differentiation toward osteocytic lineage. Enhanced calcium deposition *in vitro* and upregulation of the transcript levels of bone-specific markers were demonstrated, indicating that these scaffolds provided an efficient delivery device for BMP-2 and induced improved bone formation [121].

5.3 Neural tissue regeneration

Ellis-Behnke et al. initially explored the effect of self-assembling peptide nanofiber scaffold on the repair of injured brain tissue. They found in a hamster model of severed optic tract that the nanofiber scaffold could enhance regenerated axon reconnection to target tissues with sufficient density to promote functional return of vision, indicating that the nanofiber scaffold could contribute to tissue repair and restoration, and would be helpful to the central nervous system trauma [122]. Wang et al. fabricated the chitosan nano/microfiber mesh tubes with a deacetylation rate (DAc) of 93% and used them to bridge injured rat sciatic nerve, observed sufficient mechanical properties to preserve tube space and provision of a better scaffold for cell migration and attachment, and enhanced nerve regeneration [34], which further provided the evidence that nanofiber scaffold had the potential for the therapy of severe regeneration.

In recent years, Sakai et al. found that conduits reconstructed using hyaluronic acid (HA) had better cell adhesion and differentiation, through the contribution from axonal regeneration in the peripheral nerves [123]. Ding et al. also targeted the rabbit sciatic nerves damaged model to explore the tissue-engineered scaffold-mediated regenerative effect, and they found superior functionality of the nanosilver-collagen scaffold in

the adsorption to laminin and subsequent regeneration of damaged sciatic nerves [124].

5.4 Cardiac tissue regeneration

Cell-based therapies in cardiac tissue engineering represent a potential cure for patients with cardiac diseases, including myocardial infarction and heart failure. Currently, stem cell science has started to play an essential role in cardiac tissue regeneration and repair. Various stem cell graftings, including iPSC immobilization for myocardial infarction (MI) therapy, have achieved satisfactory efficacy.

Initially, it was found that injection of human ESC-derived vascular cells in a bioactive hydrogel could form capillaries in the infarcted zone in a rat model [125]. In this regard, Caspi et al. have engineered vascularized cardiac muscle using hESC-derived cardiomyocytes and hESC-derived ECs, and increased cardiomyocyte and EC proliferation, as well as the formation of vessel-like structures could be observed in engineered tissues [126]. Currently, iPSC cells have been shown to be promising for use in cardiac tissue-engineering strategies, as they can give rise to functional cardiomyocytes [127]. The use of iPSC cells would not only overcome the ethical concerns related to the use of hESCs, but it might also allow for the generation of an unlimited supply of functional, proliferative, and possibly autologous human cardiomyocytes and vascular cells, thus, overcoming any immunogenic concerns as well [128].

6 Conclusions

The advance of nanotechnology and its incorporation into other sciences, have greatly contributed to the progress of regenerative medicine, especially in controlling stem cell differentiation, modification of biocompatible materials, and the enhancement of drug delivery. Current interest of nanotechnology in the regenerative medicine field is growing at a great pace due to its capacity to mimic natural tissues. In the future, nanotechnology will be even more reliable, stable, and imaginative. Nonetheless, the nanomaterials used should be natural, non-immunogenic, and nontoxic. Before translating the findings of basic laboratory study to clinical trials, comprehensive assessment on the potential toxicity and side effects should be taken to ensure the absolute safety of our patients.

Received August 8, 2012; accepted November 26, 2012; previously published online January 16, 2013


References

- [1] Wong KK, Liu XL. Silver nanoparticles—the real “silver bullet” in clinical medicine? *Med. Chem. Commun.* 2010, 1, 125–131.
- [2] Szelenyi I. Nanomedicine: evolutionary and revolutionary developments in the treatment of certain inflammatory diseases. *Inflamm. Res.* 2012, 61, 1–9.
- [3] Armstead AL, Li B. Nanomedicine as an emerging approach against intracellular pathogens. *Int. J. Nanomedicine* 2011, 6, 3281–3293.
- [4] Chakraborty M, Jain S, Rani V. Nanotechnology: emerging tool for diagnostics and therapeutics. *Appl. Biochem. Biotechnol.* 2011, 165, 1178–1187.
- [5] Chekman IS, Ulberg ZR, Gorchakova NO, Nebesna TY, Gruzina TG, Priskoka AO, Doroshenko AM, Simonov PV. The prospects of medical application of metal-based nanoparticles and nanomaterials. *Lik. Sprava* 2011, (1–2), 3–21.
- [6] Wong KK, Cheung SO, Huang L, Niu J, Tao C, Ho CM, Che CM, Tam PK. Further evidence of the anti-inflammatory effects of silver nanoparticles. *ChemMedChem.* 2009, 4, 1129–1135.
- [7] Huang D, Zuo Y, Zou Q, Zhang L, Li J, Cheng L, Shen J, Li Y. Antibacterial chitosan coating on nano-hydroxyapatite/polyamide66 porous bone scaffold for drug delivery. *J. Biomater. Sci. Polym. Ed.* 2011, 22, 931–944.
- [8] Liu J, Deng ZS. Nano-cryosurgery: advances and challenges. *J. Nanosci. Nanotechnol.* 2009, 9, 4521–4542.
- [9] Santos SI, Mathew M, Loza-Alvarez P. Real time imaging of femtosecond laser induced nano-neurosurgery dynamics in *C. elegans*. *Opt. Express* 2010, 18, 364–377.
- [10] Cheng R, Feng F, Meng F, Deng C, Feijen J, Zhong Z. Glutathione-responsive nano-vehicles as a promising platform for targeted intracellular drug and gene delivery. *J. Control. Release* 2011, 152, 2–12.
- [11] Zhao JF, Chen JY, Mi L, Wang PN, Peng Q. Enhancement of intracellular delivery of anti-cancer drugs by the Tat peptide. *Ultrastruct. Pathol.* 2011, 35, 119–123.
- [12] Kim SH, Tan JP, Fukushima K, Nederberg F, Yang YY, Waymouth RM, Hedrick JL. Thermoresponsive nanostructured polycarbonate block copolymers as biodegradable therapeutic delivery carriers. *Biomaterials* 2011, 32, 5505–5514.
- [13] He Q, Gao Y, Zhang L, Zhang Z, Gao F, Ji X, Li Y, Shi J. A pH-responsive mesoporous silica nanoparticles-based multi-drug delivery system for overcoming multi-drug resistance. *Biomaterials* 2011, 32, 7711–7720.
- [14] Kubinová S, Syková E. Nanotechnologies in regenerative medicine. *Minim. Invasive Ther. Allied Technol.* 2010, 19, 144–156.
- [15] Lee JY, Choi YS, Lee SJ, Chung CP, Park YJ. Bioactive peptide-modified biomaterials for bone regeneration. *Curr. Pharm. Des.* 2011, 17, 2663–2676.
- [16] Lionetti V, Cecchini M, Ventura C. Nanomechanics to drive stem cells in injured tissues: insights from current research and future perspectives. *Stem Cells Dev.* 2011, 20, 561–568.
- [17] Rubino CM, Bradley JS. Optimizing therapy with antibacterial agents: use of pharmacokinetic-pharmacodynamic principles in pediatrics. *Paediatr. Drugs* 2007, 9, 361–369.
- [18] López-Cabezas C, Muner DS, Massa MR, Mensa Pueyo JM. Antibiotics in endophthalmitis: microbiological and pharmacokinetic considerations. *Curr. Clin. Pharmacol.* 2010, 5, 47–54.
- [19] Dasgupta A. Advances in antibiotic measurement. *Adv. Clin. Chem.* 2012, 56, 75–104.
- [20] Miller-Kasprzak E, Jagodziński PP. Endothelial progenitor cells as a new agent contributing to vascular repair. *Arch. Immunol. Ther. Exp. (Warsz)* 2007, 55, 247–259.
- [21] Chen WH, Wang HM. Experimental research progress of warming yang and reinforcing kidney of Chinese medicine to promote the differentiation of bone marrow stromal cells. *Zhongguo Gu Shang* 2011, 24, 352–356.
- [22] Khang D, Carpenter J, Chun YW, Pareta R, Webster TJ. Nanotechnology for regenerative medicine. *Biomed. Microdevices* 2010, 12, 575–587.
- [23] Weaver CV, Garry DJ. Regenerative biology: a historical perspective and modern applications. *Regen. Med.* 2008, 3, 63–82.
- [24] Polak JM, Mantalaris S. Stem cells bioprocessing: an important milestone to move regenerative medicine research into the clinical arena. *Pediatr. Res.* 2008, 63, 461–466.
- [25] Shakesheff KM, Rose FR. Tissue engineering in the development of replacement technologies. *Adv. Exp. Med. Biol.* 2012, 745, 47–57.
- [26] Jungebluth P, Moll G, Baiguera S, Macchiarini P. Tissue-engineered airway: a regenerative solution. *Clin. Pharmacol. Ther.* 2012, 91, 81–93.
- [27] Itosaka H, Kuroda S, Shichinohe H, Yasuda H, Yano S, Kamei S, Kawamura R, Hida K, Iwasaki Y. Fibrin matrix provides a suitable scaffold for bone marrow stromal cells transplanted into injured spinal cord: a novel material for CNS tissue engineering. *Neuropathology* 2009, 29, 248–257.
- [28] Laflamme C, Rouabhia M. A medical device for prefabrication of large bone grafts in modern medicine. *Med. Hypotheses* 2011, 76, 489–491.
- [29] Koh HS, Yong T, Chan CK, Ramakrishna S. Enhancement of neurite outgrowth using nano-structured scaffolds coupled with laminin. *Biomaterials* 2008, 29, 3574–3582.
- [30] Yang CY, Huang LY, Shen TL, Yeh JA. Cell adhesion, morphology and biochemistry on nano-topographic oxidized silicon surfaces. *Eur. Cell. Mater.* 2010, 20, 415–430.
- [31] Gong Y, Ma Z, Zhou Q, Li J, Gao C, Shen J. Poly(lactic acid) scaffold fabricated by gelatin particle leaching has good biocompatibility for chondrogenesis. *J. Biomater. Sci. Polym. Ed.* 2008, 19, 207–221.
- [32] Zandi M, Mirzadeh H, Mayer C, Urch H, Eslaminejad MB, Bagheri F, Mivehchi H. Biocompatibility evaluation of nano-rod hydroxyapatite/gelatin coated with nano-HAp as a novel scaffold using mesenchymal stem cells. *J. Biomed. Mater. Res. A.* 2010, 92, 1244–1255.
- [33] Ye L, Zeng X, Li H, Ai Y. Fabrication and biocompatibility of nano non-stoichiometric apatite and poly(epsilon-caprolactone) composite scaffold by using prototyping controlled process. *J. Mater. Sci. Mater. Med.* 2010, 21, 753–760.
- [34] Wang W, Itoh S, Matsuda A, Ichinose S, Shinomiya K, Hata Y, Tanaka J. Influences of mechanical properties and permeability on chitosan nano/microfiber mesh tubes as a scaffold for nerve regeneration. *J. Biomed. Mater. Res. A.* 2008, 84, 557–566.
- [35] Fernández-Bachiller MI, Pérez C, Monjas L, Rademann J, Rodríguez-Franco MI. New tacrine-4-oxo-4H-chromene hybrids

- as multifunctional agents for the treatment of Alzheimer's disease, with cholinergic, antioxidant, and β -amyloid-reducing properties. *J. Med. Chem.* 2012, 55, 1303–1317.
- [36] Kim GH. Electrospun PCL nanofibers with anisotropic mechanical properties as a biomedical scaffold. *Biomed. Mater.* 2008, 3, 025010.
- [37] Nukavarapu SP, Kumbar SG, Brown JL, Krogman NR, Weikel AL, Hindenlang MD, Nair LS, Allcock HR, Laurencin CT. Polyphosphazene/nano-hydroxyapatite composite microsphere scaffolds for bone tissue engineering. *Biomacromolecules* 2008, 9, 1818–1825.
- [38] Mehrabian M, Nasr-Esfahani M. HA/nylon 6,6 porous scaffolds fabricated by salt-leaching/solvent casting technique: effect of nano-sized filler content on scaffold properties. *Int. J. Nanomedicine* 2011, 6, 1651–1659.
- [39] Chen J, Yu Q, Zhang G, Yang S, Wu J, Zhang Q. Preparation and biocompatibility of nanohybrid scaffolds by in situ homogeneous formation of nano hydroxyapatite from biopolymer polyelectrolyte complex for bone repair applications. *Colloids Surf. B Biointerfaces* 2012, 93, 100–107.
- [40] Zhu X, Chen J, Scheideler L, Altebaeumer T, Geis-Gerstorf J, Kern D. Cellular reactions of osteoblasts to micron- and submicron-scale porous structures of titanium surfaces. *Cells Tissues Organs* 2004, 178, 13–22.
- [41] Papenburg BJ, Bolhuis-Versteeg LA, Grijpma DW, Feijen J, Wessling M, Stamatialis D. A facile method to fabricate poly(L-lactide) nano-fibrous morphologies by phase inversion. *Acta Biomater.* 2010, 6, 2477–2483.
- [42] Romano NH, Sengupta D, Chung C, Heilshorn SC. Protein-engineered biomaterials: nanoscale mimics of the extracellular matrix. *Biochim. Biophys. Acta* 2011, 1810, 339–349.
- [43] Perumcherry SR, Chennazhi KP, Nair SV, Menon D, Afeesh R. A novel method for the fabrication of fibrin-based electrospun nanofibrous scaffold for tissue-engineering applications. *Tissue Eng. Part C Methods* 2011, 17, 1121–1130.
- [44] Barnes CP, Sell SA, Boland ED, Simpson DG, Bowlin GL. Nanofiber technology: designing the next generation of tissue engineering scaffolds. *Adv. Drug Deliv. Rev.* 2007, 59, 1413–1433.
- [45] Tran PA, Zhang L, Webster TJ. Carbon nanofibers and carbon nanotubes in regenerative medicine. *Adv. Drug Deliv. Rev.* 2009, 61, 1097–1114.
- [46] Murugan R, Ramakrishna S. Design strategies of tissue engineering scaffolds with controlled fiber orientation. *Tissue Eng.* 2007, 13, 1845–1866.
- [47] Yoo HS, Kim TG, Park TG. Surface-functionalized electrospun nanofibers for tissue engineering and drug delivery. *Adv. Drug Deliv. Rev.* 2009, 61, 1033–1042.
- [48] Zhang YZ, Su B, Venugopal J, Ramakrishna S, Lim CT. Biomimetic and bioactive nanofibrous scaffolds from electrospun composite nanofibers. *Int. J. Nanomedicine* 2007, 2, 623–638.
- [49] Sahoo S, Ang LT, Goh JC, Toh SL. Growth factor delivery through electrospun nanofibers in scaffolds for tissue engineering applications. *J. Biomed. Mater. Res. A.* 2010, 93, 1539–1550.
- [50] Liu T, Xu J, Chan BP, Chew SY. Sustained release of neurotrophin-3 and chondroitinase ABC from electrospun collagen nanofiber scaffold for spinal cord injury repair. *J. Biomed. Mater. Res. A.* 2012, 100, 236–242.
- [51] Yang X, Shah JD, Wang H. Nanofiber enabled layer-by-layer approach toward three-dimensional tissue formation. *Tissue Eng. Part A.* 2009, 15, 945–956.
- [52] Horne MK, Nisbet DR, Forsythe JS, Parish CL. Three-dimensional nanofibrous scaffolds incorporating immobilized BDNF promote proliferation and differentiation of cortical neural stem cells. *Stem Cells Dev.* 2010, 19, 843–852.
- [53] Hurley JR, Balaji S, Narmoneva DA. Complex temporal regulation of capillary morphogenesis by fibroblasts. *Am. J. Physiol. Cell Physiol.* 2010, 299, C444–C453.
- [54] Gelain F, Unsworth LD, Zhang S. Slow and sustained release of active cytokines from self-assembling peptide scaffolds. *J. Control. Release* 2010, 145, 231–239.
- [55] Davis ME, Hsieh PC, Takahashi T, Song Q, Zhang S, Kamm RD, Grodzinsky AJ, Anversa P, Lee RT. Local myocardial insulin-like growth factor 1 (IGF-1) delivery with biotinylated peptide nanofibers improves cell therapy for myocardial infarction. *Proc. Natl. Acad. Sci. USA* 2006, 103, 8155–8160.
- [56] Segers VF, Tokunou T, Higgins LJ, MacGillivray C, Gannon J, Lee RT. Local delivery of protease-resistant stromal cell derived factor-1 for stem cell recruitment after myocardial infarction. *Circulation* 2007, 116, 1683–1692.
- [57] Krishna OD, Kiick KL. Protein- and peptide-modified synthetic polymeric biomaterials. *Biopolymers* 2010, 94, 32–48.
- [58] Fedorovich NE, Alblas J, Hennink WE, Oner FC, Dhert WJ. Organ printing: the future of bone regeneration? *Trends Biotechnol.* 2011, 29, 601–606.
- [59] Butscher A, Böhner M, Hofmann S, Gauckler L, Müller R. Structural and material approaches to bone tissue engineering in powder-based three-dimensional printing. *Acta Biomater.* 2011, 7, 907–920.
- [60] Lavker RM, Sun TT. Epidermal stem cells: properties, markers, and location. *Proc. Natl. Acad. Sci. USA* 2000, 97, 13473–13475.
- [61] Alonso L, Fuchs E. Stem cells of the skin epithelium. *Proc. Natl. Acad. Sci. USA* 2003, 100(Suppl 1), 11830–11835.
- [62] Aberdam D. Derivation of keratinocyte progenitor cells and skin formation from embryonic stem cells. *Int. J. Dev. Biol.* 2004, 48, 203–206.
- [63] Lau K, Paus R, Tiede S, Day P, Bayat A. Exploring the role of stem cells in cutaneous wound healing. *Exp. Dermatol.* 2009, 18, 921–933.
- [64] Taylor G, Lehrer MS, Jenson PJ, Sun TT, Lavker RM. Involvement of follicular stem cells in forming not only the follicle but also the epidermis. *Cell* 2000, 102, 451–461.
- [65] Ito M, Liu Y, Yang Z, Nguyen J, Liang F, Morris RJ, Cotsarelis G. Stem cells in the hair follicle bulge contribute to wound repair but not to homeostasis of the epidermis. *Nat. Med.* 2005, 11, 1351–1354.
- [66] Sellheyer K, Krahl D. Skin mesenchymal stem cells: prospects for clinical dermatology. *J. Am. Acad. Dermatol.* 2010, 63, 859–865.
- [67] Zabierowski SE, Fukunaga-Kalabis M, Li L, Herlyn M. Dermis-derived stem cells: a source of epidermal melanocytes and melanoma? *Pigment Cell Melanoma Res.* 2011, 24, 422–429.
- [68] Toma JG, Akhavan M, Fernandes KJ, Barnabé-Heider F, Sadikot A, Kaplan DR, Miller FD. Isolation of multipotent adult stem cells from the dermis of mammalian skin. *Nat. Cell Biol.* 2001, 3, 778–784.
- [69] Riekestina U, Muceniece R, Cakstina I, Muiznieks I, Ancans J. Characterization of human skin-derived mesenchymal stem cell proliferation rate in different growth conditions. *Cytotechnology* 2008, 58, 153–162.
- [70] Nguyen BC, Lefort K, Mandinova A, Antonini D, Devgan V, Della Gatta G, Koster MI, Zhang Z, Wang J, Tommasi di Vignano A,

- Kitajewski J, Chiorino G, Roop DR, Missero C, Dotto GP. Cross-regulation between Notch and p63 in keratinocyte commitment to differentiation. *Genes Dev.* 2006, 20, 1028–1042.
- [71] Schafer M, Werner S. Transcriptional control of wound repair. *Annu. Rev. Cell Dev. Biol.* 2007, 23, 69–92.
- [72] Watt FM. Epidermal stem cells: markers, patterning and the control of stem cell fate. *Philos. Trans. R. Soc. Lond. B.* 1998, 353, 831–837.
- [73] Ouji Y, Yoshikawa M, Nishiofuku M, Ouji-Sageshima N, Kubo A, Ishizaka S. Effects of Wnt-10b on proliferation and differentiation of adult murine skin-derived CD34 and CD49f double-positive cells. *J. Biosci. Bioeng.* 2010, 110, 217–222.
- [74] Rabbani P, Takeo M, Chou W, Myung P, Bosenberg M, Chin L, Taketo MM, Ito M. Coordinated activation of Wnt in epithelial and melanocyte stem cells initiates pigmented hair regeneration. *Cell* 2011, 145, 941–955.
- [75] Silva-Vargas V, Lo Celso C, Giangreco A, Ofstad T, Prowse DM, Braun KM, Watt FM. Beta-catenin and Hedgehog signal strength can specify number and location of hair follicles in adult epidermis without recruitment of bulge stem cells. *Dev. Cell.* 2005, 9, 121–131.
- [76] Harris PJ, Takebe N, Ivy SP. Molecular conversations and the development of the hair follicle and basal cell carcinoma. *Cancer Prev. Res. (Phila)* 2010, 3, 1217–1221.
- [77] Tian J, Wong KK, Ho CM, Lok CN, Yu WY, Che CM, Chiu JF, Tam PK. Topical delivery of silver nanoparticles promotes wound healing. *ChemMedChem.* 2007, 2, 129–136.
- [78] Liu X, Lee PY, Ho CM, Lui VC, Chen Y, Che CM, Tam PK, Wong KK. Silver nanoparticles mediate differential responses in keratinocytes and fibroblasts during skin wound healing. *ChemMedChem.* 2010, 5, 468–475.
- [79] Greulich C, Kittler S, Eppler M, Muhr G, Köller M. Studies on the biocompatibility and the interaction of silver nanoparticles with human mesenchymal stem cells (hMSCs). *Langenbecks Arch. Surg.* 2009, 394, 495–502.
- [80] Wu C, Miron R, Sculean A, Kaskel S, Doert T, Schulze R, Zhang Y. Proliferation, differentiation and gene expression of osteoblasts in boron-containing associated with dexamethasone deliver from mesoporous bioactive glass scaffolds. *Biomaterials* 2011, 32, 7068–7078.
- [81] Hosseinkhani H, Hosseinkhani M, Hattori S, Matsuoka R, Kawaguchi N. Micro and nano-scale in vitro 3D culture system for cardiac stem cells. *J. Biomed. Mater. Res. A.* 2010, 94, 1–8.
- [82] Silva GA, Czeisler C, Niece KL, Beniash E, Harrington DA, Kessler JA, Stupp SI. Selective differentiation of neural progenitor cells by high-epitope density nanofibers. *Science* 2004, 303, 1352–1355.
- [83] Gelain F, Bottai D, Vescovi A, Zhang S. Designer self-assembling peptide nanofiber scaffolds for adult mouse neural stem cell 3-dimensional cultures. *PLoS One* 2006, 1, e119.
- [84] Srouji S, Kizhner T, Suss-Tobi E, Livne E, Zussman E. 3-D Nanofibrous electrospun multilayered construct is an alternative ECM mimicking scaffold. *J. Mater. Sci. Mater. Med.* 2008, 19, 1249–1255.
- [85] Ferreira L. Nanoparticles as tools to study and control stem cells. *J. Cell. Biochem.* 2009, 108, 746–752.
- [86] Sridharan I, Kim T, Wang R. Adapting collagen/CNT matrix in directing hESC differentiation. *Biochem. Biophys. Res. Commun.* 2009, 381, 508–512.
- [87] Chao TI, Xiang S, Chen CS, Chin WC, Nelson AJ, Wang C, Lu J. Carbon nanotubes promote neuron differentiation from human embryonic stem cells. *Biochem. Biophys. Res. Commun.* 2009, 384, 426–430.
- [88] Chao TI, Xiang S, Lipstate JF, Wang C, Lu J. Poly (methacrylic acid)-grafted carbon nanotube scaffolds enhance differentiation of hESCs into neuronal cells. *Adv. Mater.* 2010, 22, 3542–3547.
- [89] Deng W. Induced pluripotent stem cells: paths to new medicines. *EMBO Rep.* 2010, 11, 161–165.
- [90] Lee G, Chambers SM, Tomishima MJ, Studer L. Derivation of neural crest cells from human pluripotent stem cells. *Nat. Protoc.* 2010, 5, 688–701.
- [91] Liu J, Sumer H, Leung J, Upton K, Dottori M, Pébay A, Verma PJ. Late passage human fibroblasts induced to pluripotency are capable of directed neuronal differentiation. *Cell Transplant.* 2011, 20, 193–203.
- [92] Lund AW, Yener B, Stegemann JP, Plopper GE. The natural and engineered 3D microenvironment as a regulatory cue during stem cell fate determination. *Tissue Eng. Part B Rev.* 2009, 15, 371–380.
- [93] Voge CM, Stegemann JP. Carbon nanotubes in neural interfacing applications. *J. Neural Eng.* 2011, 8, 011001.
- [94] Ghaedi M, Soleimani M, Shabani I, Duan Y, Lotfi AS. Hepatic differentiation from human mesenchymal stem cells on a novel nanofiber scaffold. *Cell. Mol. Biol. Lett.* 2012, 17, 89–106.
- [95] Kam NWS, Jan E, Kotov NA. Electrical stimulation of neural stem cells mediated by humanized carbon nanotube composite made with extracellular matrix protein. *Nano Lett.* 2008, 9, 273–278.
- [96] Katti DS, Robinson KW, Ko FK, Laurencin CT. Bioresorbable nanofiber-based systems for wound healing and drug delivery: optimization of fabrication parameters. *J. Biomed. Mater. Res. B Appl. Biomater.* 2004, 70, 286–296.
- [97] Han J, Chen TX, Branford-White CJ, Zhu LM. Electrospun shikonin-loaded PCL/PTMC composite fiber mats with potential biomedical applications. *Int. J. Pharm.* 2009, 382, 215–221.
- [98] Feng K, Sun H, Bradley MA, Dupler EJ, Giannobile WV, Ma PX. Novel antibacterial nanofibrous PLLA scaffolds. *J. Control. Release.* 2010, 146, 363–369.
- [99] Said SS, Aloufy AK, El-Halfawy OM, Boraie NA, El-Khordagui LK. Antimicrobial PLGA ultrafine fibers: interaction with wound bacteria. *Eur. J. Pharm. Biopharm.* 2011, 79, 108–118.
- [100] Kong H, Jang J. Antibacterial properties of novel poly(methyl methacrylate) nanofiber containing silver nanoparticles. *Langmuir* 2008, 24, 2051–2056.
- [101] Wang C, Hickey AJ. Isoxyl aerosols for tuberculosis treatment: preparation and characterization of particles. *AAPS PharmSciTech.* 2010, 11, 538–549.
- [102] Zhang P, Shao C, Zhang Z, Zhang M, Mu J, Guo Z, Liu Y. In situ assembly of well-dispersed Ag nanoparticles (AgNPs) on electrospun carbon nanofibers (CNFs) for catalytic reduction of 4-nitrophenol. *Nanoscale* 2011, 3, 3357–3363.
- [103] Gelain F, Panseri S, Antonini S, Cunha C, Donega M, Lowery J, Taraballi F, Cerri G, Montagna M, Baldissera F, Vescovi A. Transplantation of nanostructured composite scaffolds results in the regeneration of chronically injured spinal cords. *ACS Nano* 2011, 5, 227–36.

- [104] Kolambkar YM, Dupont KM, Boerckel JD, Huebsch N, Mooney DJ, Hutmacher DW, Gulberg RE. An alginate-based hybrid system for growth factor delivery in the functional repair of large bone defects. *Biomaterials* 2011, 32, 65–74.
- [105] Khil MS, Cha DI, Kim HY, Kim IS, Bhattarai N. Electrospun nanofibrous polyurethane membrane as wound dressing. *J. Biomed. Mater. Res. B Appl. Biomater.* 2003, 67, 675–679.
- [106] Chen JP, Chiang Y. Bioactive electrospun silver nanoparticles-containing polyurethane nanofibers as wound dressings. *J. Nanosci. Nanotechnol.* 2010, 10, 7560–7564.
- [107] Ikinici G, Senel S, Akincibay H, Kaş S, Erciş S, Wilson CG, Hincal AA. Effect of chitosan on a periodontal pathogen *Porphyromonas gingivalis*. *Int. J. Pharm.* 2002, 235, 121–127.
- [108] Meng H, Chen L, Ye Z, Wang S, Zhao X. The effect of a self-assembling peptide nanofiber scaffold (peptide) when used as a wound dressing for the treatment of deep second degree burns in rats. *J. Biomed. Mater. Res. B Appl. Biomater.* 2009, 89, 379–391.
- [109] Zhou Y, Yang D, Chen X, Xu Q, Lu F, Nie J. Electrospun water-soluble carboxyethyl chitosan/poly(vinyl alcohol) nanofibrous membrane as potential wound dressing for skin regeneration. *Biomacromolecules* 2008, 9, 349–354.
- [110] Kang YO, Yoon IS, Lee SY, Kim DD, Lee SJ, Park WH, Hudson SM. Chitosan-coated poly(vinyl alcohol) nanofibers for wound dressings. *J. Biomed. Mater. Res. B Appl. Biomater.* 2010, 92, 568–576.
- [111] Zhang K, Qian Y, Wang H, Fan L, Huang C, Yin A, Mo X. Genipin-crosslinked silk fibroin/hydroxybutyl chitosan nanofibrous scaffolds for tissue-engineering application. *J. Biomed. Mater. Res. A* 2010, 95, 870–881.
- [112] Cai ZX, Mo XM, Zhang KH, Fan LP, Yin AL, He CL, Wang HS. Fabrication of chitosan/silk fibroin composite nanofibers for wound-dressing applications. *Int. J. Mol. Sci.* 2010, 11, 3529–3539.
- [113] Venugopal J, Low S, Choon AT, Sampath Kumar TS, Ramakrishna S. Mineralization of osteoblasts with electrospun collagen/hydroxyapatite nanofibers. *J. Mater. Sci. Mater. Med.* 2008, 19, 2039–2046.
- [114] Zhang L, Rodriguez J, Ruez J, Myles AJ, Fenniri H, Webster TJ. Biologically inspired rosette nanotubes and nanocrystalline hydroxyapatite hydrogel nanocomposites as improved bone substitutes. *Nanotechnology* 2009, 20, 175101.
- [115] Prabhakaran MP, Venugopal J, Ramakrishna S. Electrospun nanostructured scaffolds for bone tissue engineering. *Acta Biomater.* 2009, 5, 2884–2893.
- [116] Ngiam M, Liao S, Patil AJ, Cheng Z, Yang F, Gubler M), Ramakrishna S, Chan CK. Fabrication of mineralized polymeric nanofibrous composites for bone graft materials. *Tissue Eng. Part A* 2009, 15, 535–546.
- [117] Kim SS, Sun Park M, Jeon O, Yong Choi C, Kim BS. Poly(lactide-co-glycolide)/hydroxyapatite composite scaffolds for bone tissue engineering. *Biomaterials* 2006, 27, 1399–1409.
- [118] Kim SS, Park MS, Gwak SJ, Choi CY, Kim BS. Accelerated bonelike apatite growth on porous polymer/ceramic composite scaffolds in vitro. *Tissue Eng.* 2006, 12, 2997–3006.
- [119] Gentile P, Chiono V, Boccafroschi F, Baino F, Vitale-Brovarone C, Vernè E, Barbani N, Ciardelli G. Composite films of gelatin and hydroxyapatite/bioactive glass for tissue-engineering applications. *J. Biomater. Sci. Polym. Ed.* 2010, 21, 1207–1226.
- [120] Zou B, Chen X, Zhi W, Liu Y, Cui W, Hu S, Li X. Promoted healing of femoral defects with in situ grown fibrous composites of hydroxyapatite and poly(DL-lactide). *J. Biomed. Mater. Res. A* 2012, 100, 1407–1418.
- [121] Li C, Vepari C, Jin HJ, Kim HJ, Kaplan DL. Electrospun silk-BMP-2 scaffolds for bone tissue engineering. *Biomaterials* 2006, 27, 3115–3124.
- [122] Ellis-Behnke RG, Liang YX, You SW, Tay DK, Zhang S, So KF, Schneider GE. Nano neuro knitting: peptide nanofiber scaffold for brain repair and axon regeneration with functional return of vision. *Proc. Natl. Acad. Sci. USA* 2006, 103, 5054–5059.
- [123] Sakai Y, Matsuyama Y, Takahashi K, Sato T, Hattori T, Nakashima S, Ishiguro N. New artificial nerve conduits made with photocrosslinked hyaluronic acid for peripheral nerve regeneration. *Biomed. Mater. Eng.* 2007, 17, 191–197.
- [124] Ding T, Luo ZJ, Zheng Y, Hu XY, Ye ZX. Rapid repair and regeneration of damaged rabbit sciatic nerves by tissue-engineered scaffold made from nano-silver and collagen type I. *Injury* 2010, 41, 522–527.
- [125] Kraehenbuehl TP, Ferreira LS, Hayward AM, Nahrendorf M, van der Vlies AJ, Vasile E, Weissleder R, Langer R, Hubbell JA. Human embryonic stem cell-derived microvascular grafts for cardiac tissue preservation after myocardial infarction. *Biomaterials* 2011, 32, 1102–1109.
- [126] Caspi O, Lesman A, Basevitch Y, Gepstein A, Arbel G, Habib IH, Gepstein L, Levenberg S. Tissue engineering of vascularized cardiac muscle from human embryonic stem cells. *Circ. Res.* 2007, 100, 263–272.
- [127] Zhang J, Wilson GF, Soerens AG, Koonce CH, Yu J, Palecek SP, Thomson JA, Kamp TJ. Functional cardiomyocytes derived from human induced pluripotent stem cells. *Circ. Res.* 2009, 104, e30–e41.
- [128] Nunes SS, Song H, Chiang CK, Radisic M. Stem cell-based cardiac tissue engineering. *J. Cardiovasc. Transl. Res.* 2011, 4, 592–602.



Dr. Kenneth Wong is currently the clinical associate professor in the Department of Surgery at the University of Hong Kong. He received his clinical training in the UK before embarking on lab-based research. For the past few years, he has been focusing his basic research on nanomedicine, in particular, the use and mechanisms of nanometals in wound healing and inflammation and regenerative medicine, as well as targeted chemotherapy against childhood neuroblastoma using conjugated nanocomposite molecules.



Steven Xuelai Liu is a pediatric surgeon and is currently enrolled as a PhD student in the University of Hong Kong in the field of nanomedicine.